DUPLET PRODUCT DATA SHEET



${\mathscr O}$ Recycled Content	Up to 20%	
Range	Duplet	
Category	Colour, Shape	
Collection	Absolute Collection	
Short Code	DUP2ML	
Colour	lvory	
Finish	Satin - Chevron Left	
Wall Suitability	Internal Only	
Floor Suitability	-	
Wet Barefoot	-	
Material	Glazed Ceramic	
Classificiation	BIII	
Light Reflectance Value	70.00	
CSV	VI	

Physical Properties			
Test /	Standard	Requirement	Test Result
	Length/Width EN ISO 10545-2	±0.5%≤ ± 2mm	±0.25%
$\stackrel{\rightarrow}{{{}{}{}{}{}{$	Thickness EN ISO 10545-2	±10%≤±0.5mm	±2.5%
- +	Straightness of Sides EN ISO 10545-2	±0.3% ≤ ± 1.5mm	±0.15%
+	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	± 0.4%
$\stackrel{\flat}{\underset{\land}{}{}}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.2%
	Water Absorption EN ISO 10545-3	10% to 20%	15% to 17%
	Modulus of Rupture EN ISO 10545-4	Ave I5N/mm²	25N/mm²
*	Frost Resistance Not Applicable	N/A	Not suitable
Ä	Chemical Resistance EN ISO 10545-13	Min Class B	Class A-B (better)
A	Stain Resistance EN ISO 10545-14	Min Class 3	Class 3 (better)
	Fire Rating		Class A1 Non Combustible
kg	Weight/m² Thickness 8mm		14kg

Available Sizes

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 – 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (19/05/2024). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registed in England No. 15600432. © 2024 Johnson Tiles. All rights reserved.



